

TECHNICAL DATA SHEET

Carbon Ceramic

(70% Virgin PTFE + 25% Carbon coke + 5% Ceramic powder)

PROPERTY	TEST METHOD	UNITS	Grade NFF
Specific gravity	ASTM D4894	g/cm ³	2.08 +/- 0.05
Tensile Strength	ASTM D4894	Mpa	18
Elongation	ASTM D4894	%	60
Bulk Density	ASTM D4894	g/l	-
Hardness	NEEDLE	Shore D	65 - 67

ToseTeflon

